



WOOD MASTIC® P340

Strengthened adhesion

Powder filler with fast cure

Easy to prepare: Mix 3 doses of powder and 1 dose of water.

Pot life: 1 hour

Sanding possible: after 3 hours (20°C and 40% relative humidity)

Hardness Shore: 53

Peel strength: 15kgf/cm² NFT 30-062

High quality repair with a good adhesion and easy to sand.

Perfect recovery of hues.

Ecological: the **Wood Mastic® P340 Strengthened adhesion** is made from vegetable glues and is prepared with water. It respects the environment and is not classified as a hazardous material.

Clean tools with water.

4 standard colors: light wood, blond wood, exotic wood, dark wood.

Special color: minimum 200kg

Packaging:

5kg or 20kg buckets.

Fiche technique diffusée par le Service technique le 06.09.08 et la Direction Commerciale. Conçu, mis au point et fabriqué en France. Les renseignements fournis par la présente Fiche Technique sont donnés de bonne foi, à titre indicatif. Ils ne sauraient en aucun cas induire une garantie de notre part, ni engager notre responsabilité lors de l'utilisation de nos produits. Cette Fiche Technique annule et remplace toutes les versions antérieures.



SAS au capital de 600 000 euros
Zi - Chemin des Anguillaires - 31410 NOE - France
Tél : 05.61.98.40.88 - Fax : 05 62 01 39 50
E-mail : info@briancon-production.com
Site internet : www.briancon-production.com
RC 84B600 - Siret 330 201 138 00030 - n° TVA : FR44 330 201 138